

804436 K-VC100	nd	1.80400	$\nu_d$	43.6	nF-nC	0.01844
	ne	1.80838	$\nu_e$	43.3	nF'-nC'	0.01865

屈折率 Refractive Indices		
n1548	1548.1	1.77411
n1309	1308.5	1.77834
nt	1014.0	1.78441
nA'	768.2	1.79235
nr	706.5	1.79541
nC	656.3	1.79849
nC'	643.8	1.79936
nD	589.3	1.80384
nd	587.6	1.80400
ne	546.1	1.80838
nF	486.1	1.81693
nF'	480.0	1.81801
ng	435.8	1.82731
nh	404.7	1.83610
ni	365.0	1.85150

分散式の常数 Constants of Dispersion Formula	
A0	3.1712789
A1	$-1.4900418 \times 10^{-2}$
A2	$2.8162431 \times 10^{-2}$
A3	$8.3037332 \times 10^{-4}$
A4	$-1.8683781 \times 10^{-5}$
A5	$2.6807865 \times 10^{-6}$

dn/dTの分散常数 Constants of Dispersion dn/dT abs.	
D0	$4.79 \times 10^{-6}$
D1	$1.51 \times 10^{-8}$
D2	$-1.35 \times 10^{-10}$
E0	$6.25 \times 10^{-7}$
E1	$7.77 \times 10^{-10}$
$\lambda_{TK} (\mu m)$	0.229

部分分散および部分分散比 Partial Dispersions and Relative Partial Dispersions			
nC-nt	nC-nA'	nd-nC	ne-nC
0.01408	0.00614	0.00551	0.00989
$\theta_{C,t}$	$\theta_{C,A'}$	$\theta_{d,C}$	$\theta_{e,C}$
0.764	0.333	0.299	0.536
ng-nd	ng-nF	nh-ng	ni-ng
0.02331	0.01038	0.00879	0.02419
$\theta_{g,d}$	$\theta_{g,F(\Delta)}$	$\theta_{h,g}$	$\theta_{i,g}$
1.264	0.563 (-0.0079)	0.477	1.312
nC'-nt	ne-nC'	nF'-ne	ni-nF'
0.01495	0.00902	0.00963	0.03349
$\theta'_{C,t}$	$\theta'_{e,C'}$	$\theta'_{F',e}$	$\theta'_{i,F'}$
0.802	0.484	0.516	1.796

機械的性質 Mechanical Properties		熱的性質 Thermal Properties	
ヌープ硬さ Hk Knoop Hardness	728 (7)	転移点 Tg (°C) Transformation Point	570
ビッカース硬さ Hv Vickers Hardness	723	屈伏点 At (°C) Yielding Point	609
摩耗度 Ha Abrasion	65	線膨張係数 $\alpha (\times 10^{-7} \text{°C}^{-1})$ Thermal Expansion	
ヤング率 E ( $\times 10^8 \text{N}\cdot\text{m}^{-2}$ ) Young's Modulus	1181	(-30~+70°C) 58 (+100~+300°C) 72	
剛性率 G ( $\times 10^8 \text{N}\cdot\text{m}^{-2}$ ) Modulus of Rigidity	458	熱伝導率 $\lambda (\text{W}\cdot\text{m}^{-1}\cdot\text{K}^{-1})$ Thermal Conductivity	0.803
ポアソン比 $\sigma$ Poisson Ratio	0.288	比熱 Cp ( $\text{J}\cdot\text{kg}^{-1}\cdot\text{K}^{-1}$ ) Specific Heat	500
化学的性質 Chemical Properties		その他 Other Properties	
耐水性(粉末法) RW Water Resistance	1	泡 B Bubbles	
耐酸性(粉末法) RA Acid Resistance	3	着色度 C Coloration	40/34
耐久性(表面法) DW Chemical Durability	1	比重 S.g Specific Gravity	4.71
備考 Remarks		生産頻度 PF Production frequency	

内部透過率 $\tau$ Internal Transmittance		
$\lambda(\text{nm})$	3mm	10mm
270		
280		
290		
300		
310		
320		
330	0.253	
340	0.563	0.148
350	0.782	0.440
360	0.891	0.681
370	0.941	0.819
380	0.966	0.892
390	0.978	0.931
400	0.985	0.951
420	0.990	0.969
440	0.993	0.978
460	0.995	0.983
480	0.996	0.988
500	0.997	0.991
550	0.998	0.993
600	0.997	0.993
650	0.998	0.993
700	0.998	0.995
800	0.999	0.997
1060	0.999	0.999
1500	0.998	0.997
2000	0.991	0.971

屈折率の温度係数 Temperature Coefficients of Refractive Index						
(°C)	(dn/dT)rel. ( $\times 10^{-6} \text{°C}^{-1}$ )			(dn/dT)abs. ( $\times 10^{-6} \text{°C}^{-1}$ )		
	1548.1	d	g	1548.1	d	g
-40/-20	3.9	5.0	6.5	1.5	2.6	4.0
0/+20	4.6	5.9	7.5	2.8	4.1	5.7
+40/+60	4.7	6.1	8.0	3.4	4.8	6.5